

304 Chemical Properties

	% C	% Si	% Mn	% P	%S	% Ni	% Cr	% N	% Mo
MIN. %	-	-	-	-	-	8.000	18.000	-	N/A
MAX. %	0.080	0.750	2.000	0.045	0.030	10.500	20.000	0.100	N/A

Low Carbon/304L Chemical Properties

	% C	% Si	% Mn	% P	%S	% Ni	% Cr	% N	% Mo
MIN. %	-	-	-	-	-	8.000	18.000	-	N/A
MAX. %	0.030	0.750	2.000	0.045	0.030	10.500	20.000	0.100	N/A