

316/316L Chemical Properties

	% C	% Si	% Mn	% P	%S	% Ni	% Cr	% N	% Mo
MIN. %	-	-	-	-	-	10.000	16.000	-	2.000
MAX. %	0.030	0.750	2.000	0.045	0.030	14.000	18.000	0.100	3.000